

CLAIMS

1. A bubbling-resistant laminate sheet comprising:

(A) a bubbling-resistant sheet which comprises a film having a moisture-transmission rate α measured according to JIS Z-0208 B method, and a layer of a bubbling-resistant adhesive layer provided on the back face of said film, and

(B) a functional sheet which comprises a functional film having a moisture-transmission rate β measured according to JIS Z-0208 B method, and a layer of an adhesive provided on the back face of said functional film, and which is provided on said bubbling-resistant sheet with the back face of said functional sheet facing the front face of said bubbling-resistant sheet,

wherein said moisture-transmission rate β is equal to or larger than said moisture-transmission rate α ($\alpha \leq \beta$).

2. The bubbling-resistant laminate sheet according to claim 1, wherein no bubble is observed at an interface between said bubbling-resistant laminate sheet and a polycarbonate resin substrate, after said bubbling-resistant laminate sheet is laminated on said polycarbonate resin substrate and heated in an oven set at 65°C for 24 hours.

3. A bubbling-resistant laminate member comprising a resin substrate and a bubbling-resistant laminate sheet according to claim 1 or 2 laminated on said resin substrate.